

GRANULATED CALCIUM LIME

Product Specification

EU legislation for liming material changed in May 2013, and producers must now declare total calcium content, neutralising value and fineness of all natural liming material.

Calcifert Lime meets or exceeds the specifications for fine quality liming material across all criteria.

	Minimum requirements (for fine quality limestone)	Calcifert Granulated Lime
Total Calcium (Ca)		39%
Neutralising value	50	54
Fineness	at least 97% to pass through a 2mm sieve	> 99%
	at least 80% to pass through a 1mm sieve	> 99%
	at least 50% to pass through a 0.315mm sieve	> 99%
	at least 30% to pass through a 0.1mm sieve	> 84%
Optional declarations		
Total Magnesium (Mg)		< 0.5%
Reactivity		97%
Moisture		< 0.5%
Soil incubation results		TBC

info@calcifert.co.uk | 0800 6226023 | www.calcifert.co.uk